STATUS OF CLAIMS

- 1. (Currently Amended.) An optically clear lens having antimicrobial properties comprising more than about 0.01 weight percent silver, where said lens is formed by incorporating silver having an average particle size of about 2 to about 8 microns into a lens polymer, forming said clear lens from said lens polymer and treating said clear lens with an oxidizing agent activated by treatment with an oxidizing agent.
- 2. (Original.) The lens of claim 1 wherein, the lens is a soft contact lens.
- (Currently Amended.) The lens of claim 1 wherein, the lens polymer is a silicone hydrogel.
- 4. (Original.) The lens of claim 1 having about 0.02 to about 0.2 weight percent activated silver.
- 5. (Original.) The lens of claim 1 having about 0.05 to about 0.2 weight percent activated silver.
- 6. (Currently Amended.) The lens of claim 1 wherein, the lens polymer is a silicone hydrogel having about 0.02 to about 0.1 weight percent activated silver.
- 7. (Currently Amended.) The lens of claims 6, 5, or 4 wherein the lens polymer is lenefilcon A, aquafilcon A, etafilcon A, genfilcon A, balifilcon A, polymacon, or lotrafilcon A.
- 8. (Currently Amended.) A method of reducing a lens wearer's adverse microbial reactions comprising, the step of providing an optically clear lens having antimicrobial properties, the lens comprising more than about 0.01 weight percent silver, where said lens is formed by incorporating silver having an average particle size of about

2 to about 8 microns into a lens polymer, forming said clear lens from said lens polymer and treating said clear lens with an oxidizing agent activated by treatment with an oxidizing agent.

- 9. (Original.) The method of claim 8 wherein the lens is a contact lens.
- 10. (Original.) The method of claim 8 wherein, the lens has about 0.02 to about 0.2 weight percent activated silver.
- 11. (Currently Amended.) The method of claim 8 wherein, the lens polymer is a silicone hydrogel having about 0.05 to about 0.1 percent activated silver.
- hydrogel lens having antimicrobial properties comprising more than about 0.01 weight percent activated silver, where the method comprises the step steps of, incorporating silver having an average particle size of about 2 to about 8 microns into a lens polymer, forming said clear hydrogel lens from said lens polymer and treating a said clear hydrogel lens containing silver with an oxidizing agent.
- 13. (Original.) The method of claim 12 wherein, the oxidizing agent is selected from the group consisting of hydrogen peroxide, sodium hypochlorite, peroxy acids, bromine, chlorine, chromic acid, potassium permanganate and iodine.
- 14. (Original.) The method of claim 12 wherein the oxidizing agent is sodium hypochlorite.

Claims 15 and 16 have been canceled.

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

BLACK BORDERS

IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

FADED TEXT OR DRAWING

BLURRED OR ILLEGIBLE TEXT OR DRAWING

SKEWED/SLANTED IMAGES

COLOR OR BLACK AND WHITE PHOTOGRAPHS

GRAY SCALE DOCUMENTS

LINES OR MARKS ON ORIGINAL DOCUMENT

REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

IMAGES ARE BEST AVAILABLE COPY.

OTHER:

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.